

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Application No.:

Filing Date:

Inventor

Dieter GIRLICH et al.

Title:

Method and Device for the Production of Reticular Structures

Art Unit:

Examiner:

Attorney Docket No.: 02-013

To: Commissioner for Patents
Washington, D.C. 20231

PRELIMINARY AMENDMENT
FILED CONCURRENTLY WITH UTILITY PATENT APPLICATION

Dear Sir:

Please amend the application being filed with this petition as follows:

IN THE SPECIFICATION:

Method and Device for the Production of Reticular Structures

[1] This application claims priority under 35 U.S.C. § 119 of the parent application DE 199 39 155.6, filed on August 20, 1999 and PCT application PCT/DE00/02597, filed on August 4, 2000.

BACKGROUND OF THE INVENTION

[2] This invention relates to a method of producing reticular structures, and particularly, to the production of metallic reticular structures, as well as to a device suitable therefor.

[3] Reticular structures made from metal and other materials have a wide range of application. For example, these structures can be used as lightweight structural components, battery plates, electrochemical anodes and cathodes, filters for fluids, separation devices for fluid media, heat shields, and for numerous other applications.

[4] Numerous methods for producing such types of structures are known. Automated production of such reticulated structures, however, is extremely difficult to implement, primarily because, with the conventional methods, the reticulated foam bodies that serve as patterns or pre-structures must be bonded to wax plates. The step of bonding a foam pre-structure to a wax plate is almost impossible to automate. The bonding points are, however, indispensable, since it is through these points that the foam pattern is burned out and then, through the resulting junctions that the molten metal flows into the cavities or voids formed by the foam pre-structure.

[5] US Patent 3,616,841 (Walz; issued 1971), which is viewed as the closest prior art, discloses a method for the production of an insoluble foam material with a predetermined reticulated structure. This method encompasses the steps of producing a self-supporting reticulated polyurethane foam; producing a refractory mold material by filling the voids of the polyurethane foam with a watery gypsum plaster suspension that then sets; heating the refractory mold material to a temperature of about 120° C (250° F) over a time period of two hours; producing voids in the refractory mold material by raising the temperature of the refractory mold material to between 535 and 815° C (between 1,000 and 1,500° F), in order to completely vaporize the foam and produce a mold; introducing a molten substance into the refractory mold in an amount sufficient to fill the voids which had been previously occupied by the reticulated foam pre-structure; solidifying the molten substance by reducing the temperature to below the melting point of the substance; and washing out the material that constitutes the refractory mold material. The molten substance comprises metals, metal alloys, ceramics and/or cermet.

[6] The method disclosed by Walz has several disadvantages. The equipment required for melting the substance that is poured into the refractory mold is either

very expensive, especially for melting high-melting-point metals, or is technically not feasible. Another disadvantage is that in an automated process it is very difficult to control the bonding of the foam to the wax plate. This step is critical, however, for controlling the quality of the final product, as the quality of the bonding between foam and wax plate determines the structure of the foam pre-structure, which, in turn, determines the technical parameters such as surface smoothness or dimensional accuracy, of the end product. Thus, in order to reliably obtain an end product that corresponds to specification with regard to surface smoothness or dimensional accuracy or other parameters, it is imperative that this step be controllable in order to restrict the statistical range of fluctuation in the structure of the foam as much as possible.

[7] To form the reticular structure, molten metal is poured into the refractory mold, which consists of branched voids. With the Walz method, in order to ensure that the molten metal remains liquid long enough to flow through the branches and completely fill the voids, the mold material must be heated to a temperature higher than that of the melting point of the molten metal. As a result, the solidification of the molten metal progresses very slowly, resulting in a solidified metal with a coarse grainy texture and reduced strength properties.

[8] To solve this problem, Walz suggests various cooling methods, such as, for example, spraying the mold with water or air. A problem with such cooling methods is that the mold hinders the flow of heat, thereby significantly diminishing the cooling effect. Moreover, the production of massive or solid areas of metal together with the reticular structure is related to the problem of a very slow cooling progress. In order to obtain a bubble-free and fine-grained texture, it is imperative that the solidification process of the reticular structure be a controlled process. The method steps disclosed in Walz do not provide a means for effective control over the solidification process. The Walz method has an inherent economic disadvantage that limits the success or feasibility of automating production processes for reticular structures, in that the slow progression of the solidification of the metal results in long process times.

[9] What is needed, therefore, is an automated method of production of reticular structures, particularly, metallic reticular structures. What is further needed, is such a method that produces a reticular structure having a fine-grained and bubble-free texture. What is yet further needed is such a method that allows large-scale production of metallic reticular structures, including large-dimensioned reticular structures.

SUMMARY OF THE INVENTION

[10] For the reasons cited above, it is an objective of the present invention to simplify the production of a reticular structure so as to enable automated production.

It is a further objective to enable large-scale production of reticular structures, including metallic and/or large-dimensioned reticular structures. It is a yet further objective to enable production of reticular structures having a fine-grained, bubble-free texture.

[11] The objectives are achieved according to the present invention by providing an automated method of producing reticular structures, including large-scale production of metallic and/or large-dimensioned reticular structures and by providing a device for the production of same.

[12] With the method of the present invention, a foam pattern or pre-structure is used to create a refractory mold. The foam pre-structure is placed in a refractory container and infiltrated with a refractory mold material, typically a gypsum plaster suspension. After the mold material has solidified, the resulting mold, including pre-structure, is withdrawn from the refractory container and the pre-structure removed from the mold by volatilization. The mold is then pre-heated to a temperature greater than the melting point of the molten substance that will form the reticular structure and placed inside a heat-resistant container. The molten substance for metallic reticular structures may comprise metals, alloys, ceramics, cermet materials, and/or any suitable combination thereof.

even heating of the refractory mold. Ready access to the ligaments and cells of the foam structure also promotes rapid volatilization of the foam pre-structure. After the pre-structure has been volatilized, it is also easier to monitor whether the ligaments provide sufficient means of access of the molten metal to the internal structure, that is, to the „negative mold.”

[16] The method according to the invention does not require the use of the wax plates to bond the foam pre-structure, as do conventional methods, and allows continuous automated, large-scale production of reticular structures. Examples of suitable uses of the metallic reticular structures obtained from the production method according to the invention, include use as catalysts for EMC shielding and in batteries. For example, in the production of a reticular structure for use in a catalytic converter for the combustion stabilization of diesel fuel, the refractory mold is filled with a molten metal comprising a Zn/Cu alloy. Reticular structures produced according to the method of the invention and made of aluminum and then coated with lead are used, for example, in batteries.

BRIEF DESCRIPTION OF THE DRAWINGS

[17] FIG. 1 illustrates the foam pre-structure that can also be coated.

[18] FIG. 2 shows the openable container with cover, in which the foam pre-structure is placed according to the method of the present invention.

[19] FIG. 3 shows the openable container containing the foam pre-structure, whereby the openable container has been filled with the refractory mold material .

[20] FIG. 4 shows the refractory mold material with the foam pre-structure.

[21] FIG. 5 shows a refractory mold and the cavities that remain when the foam pre-structure has been removed from the set mold material.

[22] FIG. 6 shows the device according to the present invention, including a cooling plate.

[23] FIG. 7 shows the device of FIG. 6 on the cooling plate, with the refractory mold placed in the device, the heat-resistant container, whereby the refractory mold is geometrically smaller than the device.

[24] FIG. 8 shows the reticular structure, formed according to the method and device of the present invention, with a partial jacket casting abutting the reticular structure.

DETAILED DESCRIPTION OF THE INVENTION

[25] To form a reticular structure 22 according to the method of the present invention, a reticulated foam pre-structure 10 is placed in an openable container 12 having a container lid 12A, as illustrated by FIGS. 1 and 2. Preferably, the material used for the pre-structure material 10 is polyurethane foam, although any material that provides a sufficient number of pores is suitable for use as the pre-structure material. The foam pre-structure 10 is then infiltrated with a refractory mold material 14, as shown in FIG. 3. The container lid 12A is closed for applying a vacuum to the openable container 12. The refractory mold material 14 is allowed to solidify to form a refractory mold 16. Preferably, the refractory mold material 14 is a watery gypsum plaster suspension.

[26] The surface of the foam pre-structure 10 is modifiable, preferably by roughening or structuring the surface of the foam pre-structure 10 after it has been placed in the openable container 12. Pneumatic or vacuum assistance may be used to force the refractory mold material 14 into the container 12 to ensure that the material 14 completely encases the pre-structure 10.

[27] After solidification, the refractory mold 16, along with the foam pre-structure 10, shown in FIG. 4, is withdrawn from the openable container 12, and the foam pre-structure 10 stripped or removed from the refractory mold 16. FIG. 5 shows the refractory mold 16, including the voids 17 formed by the foam pre-structure 10.

[28] FIG. 6 shows the device according to the present invention, which is a heat-resistant container 18 mounted on a cooling plate 20. The refractory mold 16 is pre-

heated and placed into the heat-resistant container 18. As shown in FIG. 7, the heat-resistant container 16 is geometrically larger than the mold 16. The difference in dimensions between the heat-resistant container 18 and the mold 16 results in a gap 19 between the mold 16 and the heat-resistant container 18. The mold 16 is then infiltrated with a molten substance that fills the voids 19 in the mold 16, thereby forming a reticular structure 22, as shown in FIG. 8. Any suitable casting material may be used in the method according to the present invention. For metallic reticular structures, the molten substance comprises preferably metals, alloys, ceramics, metal ceramics, and/or any suitable combination thereof. After the molten substance has solidified, the reticular structure 22 is withdrawn from the heat-resistant container 18 and the refractory mold 16 removed from the structure 16.

[29] As can be seen in FIG. 8, the reticular structure 22 corresponds in shape to the foam pre-structure 10. Also shown in FIG. 8 is a plate 24 that is formed when a casting material is poured over the mold 16 that is filled with the molten substance and fills the gap 19 between the heat-resistant container 18 and the mold 16.

[30] The heat-resistant container 18 according to the invention holds the mold 16 and has at least one opening 21 for pouring the molten metal into the refractory mold 16. Preferably, the interior space of the container 18 is larger than the pre-heated refractory mold 16 filled with the molten substance, in order to provide a gap between the wall of the container and the refractory mold. The size of the gap is freely-selectable and is determined by the difference in size between the heat-resistant container 18 and the filled, pre-heated mold 16. After pouring the molten substance into the mold 16, a solid jacket or shell is then cast onto the structure, i.e., the mold 16 filled with the molten substance, thereby filling the gap 19 between the structure and the container 18. The container 18 is temperature-controlled and maintained at a temperature that is cooler than that of the molten metal and the pre-heated refractory mold 16. Since the jacket is in direct contact with the container 18, heat is drawn from the casting metal directly into the container 18 during the solidification process, allowing the structure 22 to cool from the outside inward toward the center of the mold 18, thereby producing a cast structure with a fine grain and, also, producing optimal bonding between ligaments 22A of the reticular

structure 22 and the solid shell. The reticular structure 22 that is obtained after solidification of the molten substance can then be cleaned and is modifiable, for example, by applying a conventional coating to the structure 22.

[31] The reticular structures 22 produced by the method according to the invention, including the use of the heat-resistant container 18, can be integrated into castings that are produced by various casting methods, such as, for example, die casting, permanent-mold casting, centrifugal casting, low-pressure casting or back-pressure casting. The reticular structures themselves can also be cast by these methods.

[32] The method according to the invention enables automated production of reticular structures 22 of the most varying degrees of fineness with respect to the thickness of ligaments 22A and the size of cells 22B. Combinations of various cell sizes and ligament thicknesses within one structure 22 are also possible.

[33] The method and device according to the invention described herein are merely illustrative of the present invention. It should be understood that variations in the steps of the method and construction of the device may be contemplated in view of the following claims without straying from the intended scope and field of the invention herein disclosed.

IN THE CLAIMS:

Please amend Claim 1 as follows:

1. A method of producing a reticular structure, said method comprising the steps of:
 - a) placing a reticulated foam pre-structure into a first container having a lid;
 - b) infiltrating said foam pre-structure with a refractory mold material;
 - c) solidifying said refractory material to form a refractory mold;
 - d) withdrawing said refractory mold along with said foam pre-structure from said first container;
 - e) removing said foam pre-structure from said refractory mold;
 - f) pre-heating said refractory mold and placing said mold into a second container;
 - g) infiltrating said refractory mold with a molten substance to form a reticular structure;
 - h) after said molten substance has solidified, withdrawing said reticular structure from said second container and removing said refractory mold from said reticular structure.

Please cancel Claims 2 - 7.

Please add Claims 8 - 18 as follows:

8. The method of producing a reticular structure according to claim 1, wherein, after the step of withdrawing said refractory mold from said first container, said foam pre-structure protrudes from said refractory mold.
9. The method of producing a reticular structure according to claim 1, wherein, subsequent to the step of infiltrating said refractory mold with said molten substance, said method includes the step of casting a solid jacket on said refractory mold with said molten substance.

10. The method of producing a reticular structure according to claim 1, wherein said foam pre-structure has a surface and wherein, subsequent to step a), said method includes a step of modifying said surface by roughening.

11. The method of producing a reticular structure according to claim 1, wherein said foam pre-structure has a surface and wherein, subsequent to step a), said method includes a step of modifying said surface by texturing.

12. The method of producing a reticular structure according to claim 1, wherein said reticular structure has a structure surface and wherein, subsequent to step h), said method includes a step of modifying said structure surface by applying a coating to said structure surface.

13. A device for producing a reticular structure according to claim 1, wherein said second container has a container wall and at least one opening for pouring in said molten substance, and has an interior space that is sufficiently large to provide a gap between said pre-heated refractory mold filled with said molten substance and said container wall.

14. The method of Claim 1, wherein said reticular structure is a metallic reticular structure and said molten substance is a molten metallic substance comprising materials from a group consisting of metals, metal alloys, ceramics and cermet.

15. The method of Claim 1, wherein said foam pre-structure is a polyurethane foam.

16. The method of Claim 1, wherein said refractory mold material comprises a gypsum plaster suspension.

17. The method of Claim 1, wherein said first container is made of a refractory material.

18. The method of Claim 1, wherein said second container is made of a heat-resistant material.

2009-03-02 10:07:33

IN THE ABSTRACT:

ABSTRACT

A method of producing reticular structures, particularly metallic reticular structures, as well as a device suitable for the production thereof. The method and device enable continuous and/or automated production of such structures, and particularly, large-scale automated production of large-dimensioned reticular structures. A reticulated foam pre-structure is placed into a first container and infiltrated with a refractory material. After solidification, the mold formed by the refractory material is removed from the first container and the foam pre-structure stripped from the mold. The mold is then pre-heated and placed into a second container and infiltrated with a molten substance that forms the reticular structure when solidified. The filled mold may be covered with a solid jacket as a means of controlling the rate and progression of solidification of the molten substance to form a fine-grained, bubble-free structure.

Remarks:


Two sheets of informal drawings that illustrate the method and the device claimed in the present application and described in the specification as filed were added to the application. The drawings are based on the information provided in the application from which priority is claimed and no new subject matter was introduced with these drawings.

The specification was amended for reasons of grammar and/or syntax, to include references to the drawings, and to bring the specification into a form that corresponds to U.S. conventions and formalities. No new subject matter was added with these amendments. A clean copy of the Specification is included with this petition and a marked-up copy attached hereto.

The claims were amended to eliminate multiple dependencies and to bring them into compliance with the U.S. rules. No new subject matter was introduced with these amendments. A clean copy of the Claims is included with this petition and a marked-up copy attached hereto.

Applicants respectfully request that the amendments to the Specification and Claims, and the new drawings be entered in the application.

Respectfully submitted,



Patricia M. Mathers
Attorney for Applicants
Reg. No. 44,906
Thomas L. Bohan & Associates
371 Fore Street
Portland, ME 04101
(207) 773-3132

February 20, 2002

Enclosed:
Substitute Specification
Marked-up copy of Specification
Drawings (2 sheets)

Mailed Express Post Office to Addressee
Label No. EL 919 311 211 US
February 20, 2002

Marked-up Copy Showing Insertions and Deletions

[Process] Method and Device for the [Manufacture] Production of [Grid]
Reticular Structures

This invention [concerns the process for the manufacture of grid structures,
especially for the manufacture of metallic grid structures] relates to a method of
producing reticular structures, and particularly, to the production of metallic reticular
structures, as well as a device suitable therefor.

Reticular structures made [out of] from metal and other materials have a wide range
of application. For example, these structures can be used as lightweight structural
[building] components [with low weight], battery plates, electrochemical anodes and
cathodes, filters for fluids, separation devices for fluid media, [thermal] heat shields
and for numerous other uses.

[For the manufacture of these types of structures, numerous processes are known,
whereby however, in general an automatic fabrication is only possible with great
difficulty. The cause for this, is that with this process, the reticulated foam bodies
must be bonded with wax plates. The automated fabrication of the gluing points is
either not possible, or possible only with great difficulty.] Numerous methods for
producing such types of structures are known. Automated production of such
reticulated structures, however, is extremely difficult to implement, primarily
because, with the conventional methods, the reticulated foam bodies that serve as
patterns or pre-structures must be bonded to wax plates. The step of bonding a
foam pre-structure to a wax plate is almost impossible to automate. The [glue
points] bonding points are, however, indispensable, since [through these on the one
hand, the burning out of the foam pre-structures takes place, and on the other,
through the arising connection points, the molten bath in the hollow spaces of the
foam pre-structure flows in.] it is through these points that the foam pattern is burned

Marked-up Copy Showing Insertions and Deletions

out and then, through the resulting junctions that the molten metal flows into the cavities or voids formed by the foam pre-structure.

US [patent number] Patent 3,616,841 (Walz; issued 1971), which is viewed as the [nearest state-of-the-art technology, shows a process for the manufacture] closest prior art, discloses a method for the production of an insoluble foam material with a predetermined reticular structure. This [process] method encompasses the steps of producing [manufacture of] a self-supporting reticulated polyurethane foam; [the manufacture of an apyrous mass, in that the hollow spaces of the polyurethane foam are filled with a watery plaster-of-Paris suspension and this suspension cements] producing a refractory mold material by filling the voids of the polyurethane foam with a watery gypsum plaster suspension that then sets; [the] heating [of] the [apyrous mass] refractory mold material to a temperature of about 120° C (250° F) over a time period of two hours; [the production of hollow spaces] producing voids in the [apyrous form mass] refractory mold material by raising the temperature of the refractory mold material [, in which the temperature of the apyrous molding material is raised] to between 535 to 815° C (1,000 to 1,500° F), in order to completely vaporize all of the foam and produce a mold; introducing [, the bringing in of] a molten substance into the refractory mold in an amount sufficient to fill the voids which had been previously [, which consists of metals, metal alloys, ceramics or cement, in the apyrous molding material, whereby the amount of the substance is sufficient, in order to fill the hollow spaces, which had been] occupied by the reticulated foam pre-structure; [solidification of] solidifying the molten substance by reducing the temperature to below[, in that the temperature is so reduced, that it lies below the] melting point of the substance; and [the] washing out [of] the material that constitutes the refractory mold material. The molten substance comprises metals, metal alloys, ceramics, and/or cermet[, which the apyrous molding material constitutes. This process shows several disadvantages].

[The melting of the substance, which is brought into the apyrous molding material, demands great a instrumental expenditure especially with high melting point metals or is technically not feasible.] The method disclosed by Walz has several

disadvantages. The equipment required for melting the substance that is poured into the refractory mold is either very expensive, especially for melting high-melting-point metals, or is technically not feasible. [The structure of the foam is determined by the connection of the foams to the wax plates. The structure of the foam determines the technical parameter of the end product, so that the statistical fluctuation range must be as narrow as possible, in order to guarantee the technical parameters of the end product.] Another disadvantage is that in an automated process it is very difficult to control the bonding of the foam to the wax plate. This step is critical, however, for controlling the quality of the final product, as the quality of the bonding between foam and wax plate determines the structure of the foam pre-structure, which, in turn, determines the technical parameters such as surface smoothness or dimensional accuracy, of the end product. Thus, in order to reliably obtain an end product that corresponds to specification with regard to surface smoothness or dimensional accuracy or other parameters, it is imperative that this step be controllable in order to restrict the statistical range of fluctuation in the structure of the foam as much as possible. [Moreover, it is necessary, in order to fill the branched hollow spaces of the apyrous molding material with a molten bath, to warm the molding material to temperatures, which lie above the melting point of the substance used. This leads to the metal solidifying only very slowly, whereby the solidified metal attains a coarse grainy texture, which causes poor consistency.]

To form the reticular structure, molten metal is poured into the refractory mold, which consists of branched voids. With the Walz method, in order to ensure that the molten metal remains liquid long enough to flow through the branches and completely fill the voids, the mold material must be heated to a temperature higher than that of the melting point of the molten metal. As a result, the solidification of the molten metal progresses very slowly, resulting in a solidified metal with a coarse grainy texture and reduced strength properties.

To solve this problem, [US patent number 3,616,841] Walz suggests various cooling methods, such as, for example, spraying the mold with water or air. [The cooling effect will, however, be substantially weakened, since the molding material hinders

Marked-up Copy Showing Insertions and Deletions

the heat flow.] A problem with such cooling methods is that the mold hinders the flow of heat, thereby significantly diminishing the cooling effect. [Even the manufacture of massive metal areas in common with the grid structure is connected with the problem of the very slow cooling taking place. The given process steps hardly allow a controlled solidification of the metal, in order to attain a bubble-free and fine-grained texture.] Moreover, the production of massive or solid areas of metal together with the reticular structure is related to the problem of a very slow cooling progress. In order to obtain a bubble-free and fine-grained texture, it is imperative that the solidification process of the reticular structure be a controlled process. The method steps disclosed in Walz do not provide a means for effective control over the solidification process. The Walz method has an inherent economic disadvantage that limits the success or feasibility of automating production processes for reticular structures, in that the slow progression of the solidification of the metal results in long process times. [In any case, the slow-going solidification of the metal leads to long process times, which also stand in the way of automated fabrication.]

[Thus, it is the objective of the invention at hand, to so simplify the manufacture of grid structures, that automated fabrication of this type of structure is possible. With this, comes the task of finding a process, which allows the manufacture of grid structures with large dimensions on a large scale.]

What is needed, therefore, is an automated method of production of reticular structures, particularly, metallic reticular structures. What is further needed, is such a method that produces a reticular structure having a fine-grained and bubble-free texture. What is yet further needed is such a method that allows large-scale production of metallic reticular structures, including large-dimensioned reticular structures.

SUMMARY OF THE INVENTION

Marked-up Copy Showing Insertions and Deletions

For the reasons cited above, it is an objective of the present invention to simplify the production of a reticular structure so as to enable automated production. It is a further objective to enable large-scale production of reticular structures, including metallic and/or large-dimensioned reticular structures. It is a yet further objective to enable production of reticular structures having a fine-grained, bubble-free texture.

The objectives are achieved according to the present invention by providing an automated method of producing reticular structures, including large-scale production of metallic and/or large-dimensioned reticular structures and by providing a device for the production of same.

With the method of the present invention, a foam pattern or pre-structure is used to create a refractory mold. The foam pre-structure is placed in a refractory container and infiltrated with a refractory mold material, typically a gypsum plaster suspension. After the mold material has solidified, the resulting mold, including pre-structure, is withdrawn from the refractory container and the pre-structure removed from the mold by volatilization. The mold is then pre-heated to a temperature greater than the melting point of the molten substance that will form the reticular structure and placed inside a heat-resistant container. The molten substance for metallic reticular structures may comprise metals, alloys, ceramics, cermet materials, and/or any suitable combination thereof. [Appropriate to the invention, this is to be attained by a process encompassing the following steps:

- (1) Putting of a reticulated foam pre-structure into a hinged container;
- (2) Infiltration of the foam pre-structure with an apyrous material;
- (3) Solidification of the apyrous material;
- (4) Removal of the solidified material out of the hinged container;
- (5) Removal of the foam pre-structure from the apyrous material;
- (6) Putting of the resulting, pre-warmed body into an apyrous container;
- (7) Infiltration of the body with a molten bath;
- (8) Removal of the resulting body after solidification of the molten bath ad removal of the apyrous material.]

Marked-up Copy Showing Insertions and Deletions

A key feature of the method and device according to the present invention is that the heat-resistant container is greater in size than the size of the pre-heated mold when it is filled with the molten substance. After the mold is placed in the heat-resistant container and filled with the molten substance, a solid jacket or shell is then poured over the filled mold, filling a gap between the filled mold and the wall of the container. The container wall is temperature-controlled and maintained at a temperature that is lower than the melting point of the molten substance. Since the jacket is in direct contact with the container wall, heat is drawn from the mold through the jacket into the wall and, as a result, cooling begins at the outer perimeter and progresses inward toward the center of the mold. After the molten substance has solidified, the mold is removed from the heat-resistant container and stripped or removed from the cast reticular structure. The ability to control the temperature of the heat-resistant container and of the refractory mold promotes bubble-free solidification of the molten metal.

[Additionally, modification of the surface of the foam pre-structure can be followed by step (1). This is done preferably, by roughing or structuring of the surface of the foam pre-structure. The pouring-in of the molten bath into the apyrous container (step (7)) can take place with pneumatic or vacuum assistance. Subsequent to step (8), the grid structure attained can be cleaned and possibly modified, in that the grid structure is, for example, coated.]

The [process appropriate] method according to the invention offers several advantages. [Gluing of the foam pre-structure to the funnel system and the sprue is no longer necessary. By this, the material and time consumption on the manufacture of casting mould is substantially reduced.] It is no longer necessary to bond the foam pre-structure to the running system and sprue cup. This substantially reduces the time and material required to produce the casting mold. Because large areas of the foam pre-structure are no longer bonded to the running system, the method also eliminates an inherent source of error that resulted from the uncontrollable method of bonding the pre-structure to the running system. The method according to the invention is also economical, as only the amount of

Marked-up Copy Showing Insertions and Deletions

refractory material that is required to produce the mold for the actual reticular structure is used, thus reducing to a minimum the amount of refractory material used in the production of the reticular structure.

The method according to the invention provides additional advantages that improve the quality assurance for the structures. For example, following withdrawal from the first container, the foam pre-structure protrudes from the refractory mold. This simplifies and improves visual monitoring as to whether, after the foam pre-structure is volatilized, the ligaments and cells formed from the pre-structure will be sufficiently well set externally to ensure a complete casting of the reticular structure. Moreover, the accessibility to all sides of the foam pre-structure promotes rapid, even heating of the refractory mold. Ready access to the ligaments and cells of the foam structure also promotes rapid volatilization of the foam pre-structure. After the pre-structure has been volatilized, it is also easier to monitor whether the ligaments provide sufficient means of access of the molten metal to the internal structure, that is, to the „negative mold.“ [Furthermore, the source of errors, with which the uncontrollable gluing process is connected, lapses, since large areas of the foam pre-structure are not connected with the funnel system. Only the amount of apyrous material is needed, which is necessary in order to manufacture the grid structure.

The foam pre-structure protrudes after the removal from the mold container from the apyrous molding material. By this, it is easy to check, if after the vaporization of the foam-pre-body all cell connectors and cells have a sufficiently good external connection, in order to guarantee a complete casting. Beyond this, the accessibility of the foam pre-structure shows advantages from all sides, that the apyrous mould can be heated without delay and that free access to the cell connection and cells of the foam structure make an accelerated vaporization of the foam pre-structure possible. After the vaporization it can also easily be checked, if enough cell connections are intact for access of the molten bath to the internal structure of the „negative mould.„ Since the apyrous material is pre-warmed, before it is laid into the apyrous container, the molten mass hardens from the outside, meaning from the container wall held cooler inward. By targeted temperature guidance of the

Marked-up Copy Showing Insertions and Deletions

container and of the apyrous material, a bubble-free solidification of the molten bath can be made possible.]

The method according to the invention does not require the use of the wax plates to bond the foam pre-structure, as do conventional methods, and allows continuous auotmated, large-scale production of reticular structures. Examples of suitable uses of the metallic reticular structures obtained from the production method according to the invention, include use as catalysts for EMC shielding and in batteries. For example, in the production of a reticular structure for use in a catalytic converter for the combustion stabilization of diesel fuel, the refractory mold is filled with a molten metal comprising a Zn/Cu alloy. Reticular structures produced according to the method of the invention and made of aluminum and then coated with lead are used, for example, in batteries.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 illustrates the foam pre-structure that can also be coated.

FIG. 2 shows the first openable container with cover, in which the foam pre-structure is placed according to the method of the present invention.

FIG. 3 shows the first openable container containing the foam pre-structure, whereby the container has been filled with the refractory mold material .

FIG. 4 shows the refractory mold material with the foam pre-structure.

FIG. 5 shows a refractory mold and the cavities that remain when the foam pre-structure has been removed from the set mold material.

FIG. 6 shows the device according to the present invention, including a cooling plate.

FIG. 7 shows the device of FIG. 6 on the cooling plate, with the refractory mold placed in the device, whereby the refractory mold is geometrically smaller than the device.

FIG. 8 shows the reticular structure, formed according to the method and device of the present invention, with a partial jacket casting abutting the reticular structure.

DETAILED DESCRIPTION OF THE INVENTION

To form a reticular structure 22 according to the method of the present invention, a reticulated foam pre-structure 10 is placed in an openable container 12 having a container lid 12A, as illustrated by FIGS. 1 and 2. Preferably, the material used for the pre-structure material 10 is polyurethane foam, although any material that provides a sufficient number of pores is suitable for use as the pre-structure material. The foam pre-structure 10 is then infiltrated with a refractory mold material 14, as shown in FIG. 3. The container lid 12A is closed for applying a vacuum to the openable container 12. The refractory mold material 14 is allowed to solidify to form a refractory mold 16. Preferably, the refractory mold material 14 is a watery gypsum plaster suspension.

The surface of the foam pre-structure 10 is modifiable, preferably by roughening or structuring the surface of the foam pre-structure 10 after it has been placed in the openable container 12. Pneumatic or vacuum assistance may be used to force the refractory mold material 14 into the container 12 to ensure that the material 14 completely encases the pre-structure 10.

After solidification, the refractory mold 16, along with the foam pre-structure 10, shown in FIG. 4, is withdrawn from the openable container 12, and the foam pre-structure 10 stripped or removed from the refractory mold 16. FIG. 5 shows the refractory mold 16, including the voids 17 formed by the foam pre-structure 10.

FIG. 6 shows the device according to the present invention, which is a heat-resistant container 18 mounted on a cooling plate 20. The refractory mold 16 is pre-heated and placed into the heat-resistant container 18. As shown in FIG. 7, the heat-resistant container 16 is geometrically larger than the mold 16. The difference in dimensions between the heat-resistant container 18 and the mold 16 results in a gap 19 between the mold 16 and the heat-resistant container 18. The mold 16 is then infiltrated with a molten substance that fills the voids 19 in the mold 16, thereby forming a reticular structure 22, as shown in FIG. 8. Any suitable casting material may be used in the method according to the present invention. For metallic reticular structures, the molten substance comprises preferably metals, alloys, ceramics, metal ceramics, and/or any suitable combination thereof. After the molten substance has solidified, the reticular structure 22 is withdrawn from the heat-resistant container 18 and the refractory mold 16 removed from the structure 16.

As can be seen in FIG. 8, the reticular structure 22 corresponds in shape to the foam pre-structure 10. Also shown in FIG. 8 is a plate 24 that is formed when a casting material is poured over the mold 16 that is filled with the molten substance and fills the gap 19 between the heat-resistant container 18 and the mold 16.

Marked-up Copy Showing Insertions and Deletions

The heat-resistant container 18 according to the invention holds the mold 16 and has at least one opening 21 for pouring the molten metal into the refractory mold 16. Preferably, the interior space of the container 18 is larger than the pre-heated refractory mold 16 filled with the molten substance, in order to provide a gap between the wall of the container and the refractory mold. The size of the gap is freely-selectable and is determined by the difference in size between the heat-resistant container 18 and the filled, pre-heated mold 16. After pouring the molten substance into the mold 16, a solid jacket or shell is then cast onto the structure, i.e., the mold 16 filled with the molten substance, thereby filling the gap 19 between the structure and the container 18. The container 18 is temperature-controlled and maintained at a temperature that is cooler than that of the molten metal and the pre-heated refractory mold 16. Since the jacket is in direct contact with the container 18, heat is drawn from the casting metal directly into the container 18 during the solidification process, allowing the structure 22 to cool from the outside inward toward the center of the mold 18, thereby producing a cast structure with a fine grain and, also, producing optimal bonding between ligaments 22A of the reticular structure 22 and the solid shell. The reticular structure 22 that is obtained after solidification of the molten substance can then be cleaned and is modifiable, for example, by applying a conventional coating to the structure 22.

The reticular structures 22 produced by the method according to the invention, including the use of the heat-resistant container 18, can be integrated into castings that are produced by various casting methods, such as, for example, die casting, permanent-mold casting, centrifugal casting, low-pressure casting or back-pressure casting. The reticular structures themselves can also be cast by these methods.

The method according to the invention enables automated production of reticular structures 22 of the most varying degrees of fineness with respect to the thickness of ligaments 22A and the size of cells 22B. Combinations of various cell sizes and ligament thicknesses within one structure 22 are also possible.

Marked-up Copy Showing Insertions and Deletions

The method and device according to the invention described herein are merely illustrative of the present invention. It should be understood that variations in the steps of the method and construction of the device may be contemplated in view of the following claims without straying from the intended scope and field of the invention herein disclosed.

[This shows at least one opening for the pouring in of the molten bath into the apyrous material. Preferably, the interior space of the container is larger than the apyrous, preheated material. Between the container wall and the body made out of apyrous material, a freely-selectable gap comes into being, so that a freely formed, massive partition can be poured on the grid structure. This partition is in direct contact with the container wall, so that the solidification warmth from the casting metal can be led off directly in the container wall and a fine-granular casting metal texture is produced. Furthermore, an optimal connection of the cell connection to the grid structure on the massive partition is produced.]

[The grid structures produced by the process with the use of the apyrous container, can be integrated into castings, which can be manufactured with various casting processes, as for example, die casting, permanent-mold casting, centrifugal casting, low-pressure casting or back-pressure casting. Also, grid structures, themselves, can be casted by this process. The process can be conducted continuously, since at this technological level, the necessity of gluing wax plates to the foam pre-structure is passed upon. By the use of the process corresponding to the invention, an automated fabrication of grid structures is made possible.]

[Any material can be used as a foam pre-structure, that shows a sufficient number of pores. Preferably, this material is polyurethane foam. As an apyrous material, the employment of plaster-of-Paris is preferred. The molten bath consists of metals, metal alloys, ceramics or metal ceramics. Any casting material can be used, however.]

Marked-up Copy Showing Insertions and Deletions

[The metallic grid structures produced by the invention, can for example, be employed as catalysts for EMC shielding and in batteries. For example, for the manufacturer of a catalytic converter for the combustion stabilization of diesel fuel, a Zn/Cu alloy is used as a molten bath, with which the aporous material is filled. For example, grid structures produced by the invention can be employed in batteries, which are made out of aluminum and following step (8) can be coated with lead.]

11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65
66
67
68
69
70
71
72
73
74
75
76
77
78
79
80
81
82
83
84
85
86
87
88
89
90
91
92
93
94
95
96
97
98
99
100
101
102
103
104
105
106
107
108
109
110
111
112
113
114
115
116
117
118
119
120
121
122
123
124
125
126
127
128
129
130
131
132
133
134
135
136
137
138
139
140
141
142
143
144
145
146
147
148
149
150
151
152
153
154
155
156
157
158
159
160
161
162
163
164
165
166
167
168
169
170
171
172
173
174
175
176
177
178
179
180
181
182
183
184
185
186
187
188
189
190
191
192
193
194
195
196
197
198
199
200
201
202
203
204
205
206
207
208
209
210
211
212
213
214
215
216
217
218
219
220
221
222
223
224
225
226
227
228
229
230
231
232
233
234
235
236
237
238
239
240
241
242
243
244
245
246
247
248
249
250
251
252
253
254
255
256
257
258
259
260
261
262
263
264
265
266
267
268
269
270
271
272
273
274
275
276
277
278
279
280
281
282
283
284
285
286
287
288
289
290
291
292
293
294
295
296
297
298
299
300
301
302
303
304
305
306
307
308
309
310
311
312
313
314
315
316
317
318
319
320
321
322
323
324
325
326
327
328
329
330
331
332
333
334
335
336
337
338
339
340
341
342
343
344
345
346
347
348
349
350
351
352
353
354
355
356
357
358
359
360
361
362
363
364
365
366
367
368
369
370
371
372
373
374
375
376
377
378
379
380
381
382
383
384
385
386
387
388
389
390
391
392
393
394
395
396
397
398
399
400
401
402
403
404
405
406
407
408
409
410
411
412
413
414
415
416
417
418
419
420
421
422
423
424
425
426
427
428
429
430
431
432
433
434
435
436
437
438
439
440
441
442
443
444
445
446
447
448
449
450
451
452
453
454
455
456
457
458
459
460
461
462
463
464
465
466
467
468
469
470
471
472
473
474
475
476
477
478
479
480
481
482
483
484
485
486
487
488
489
490
491
492
493
494
495
496
497
498
499
500
501
502
503
504
505
506
507
508
509
510
511
512
513
514
515
516
517
518
519
520
521
522
523
524
525
526
527
528
529
530
531
532
533
534
535
536
537
538
539
540
541
542
543
544
545
546
547
548
549
550
551
552
553
554
555
556
557
558
559
560
561
562
563
564
565
566
567
568
569
570
571
572
573
574
575
576
577
578
579
580
581
582
583
584
585
586
587
588
589
590
591
592
593
594
595
596
597
598
599
600
601
602
603
604
605
606
607
608
609
610
611
612
613
614
615
616
617
618
619
620
621
622
623
624
625
626
627
628
629
630
631
632
633
634
635
636
637
638
639
640
641
642
643
644
645
646
647
648
649
650
651
652
653
654
655
656
657
658
659
660
661
662
663
664
665
666
667
668
669
670
671
672
673
674
675
676
677
678
679
680
681
682
683
684
685
686
687
688
689
690
691
692
693
694
695
696
697
698
699
700
701
702
703
704
705
706
707
708
709
710
711
712
713
714
715
716
717
718
719
720
721
722
723
724
725
726
727
728
729
730
731
732
733
734
735
736
737
738
739
740
741
742
743
744
745
746
747
748
749
750
751
752
753
754
755
756
757
758
759
760
761
762
763
764
765
766
767
768
769
770
771
772
773
774
775
776
777
778
779
780
781
782
783
784
785
786
787
788
789
790
791
792
793
794
795
796
797
798
799
800
801
802
803
804
805
806
807
808
809
810
811
812
813
814
815
816
817
818
819
820
821
822
823
824
825
826
827
828
829
830
831
832
833
834
835
836
837
838
839
840
841
842
843
844
845
846
847
848
849
850
851
852
853
854
855
856
857
858
859
860
861
862
863
864
865
866
867
868
869
870
871
872
873
874
875
876
877
878
879
880
881
882
883
884
885
886
887
888
889
890
891
892
893
894
895
896
897
898
899
900
901
902
903
904
905
906
907
908
909
910
911
912
913
914
915
916
917
918
919
920
921
922
923
924
925
926
927
928
929
930
931
932
933
934
935
936
937
938
939
940
941
942
943
944
945
946
947
948
949
950
951
952
953
954
955
956
957
958
959
960
961
962
963
964
965
966
967
968
969
970
971
972
973
974
975
976
977
978
979
980
981
982
983
984
985
986
987
988
989
990
991
992
993
994
995
996
997
998
999
1000

Marked-up Copy Showing Insertions and Deletions

What is claimed is:

1. A method of producing a reticular structure, said method comprising the steps
of [Process for the manufacture of metallic grid structures, by which it is qualified
that the steps cover]
 - a) placing a reticulated foam pre-structure into a first container having a lid
[Putting in of a reticulated foam pre-structure into a hinged container];
 - b) infiltrating said [infiltration of the] foam pre-structure with a refractory
mold [an apyrous] material;
 - c) solidifying said refractory material to form a refractory mold [removal of
the solidified apyrous material from the hinged container];
 - d) withdrawing said refractory mold along with said foam pre-structure from
said first container [removal of the foam pre-structure from the apyrous
material];
 - e) removing said foam pre-structure from said refractory mold;
 - f) pre-heating said refractory mold and placing said mold into a second
container [Putting in of the resulting, heated body into a heat-resistant
container];
 - g) infiltrating said refractory mold with a molten substance to form a
reticular structure [infiltration of the body with a molten bath];
 - h) after said molten substance has solidified, withdrawing said reticular
structure from said second container and removing said refractory mold
from said reticular structure [removal of the resulting body after
solidification of the molten bath from the heat-resistant container and
removal of the apyrous material].

Claims 2 - 7 are cancelled.

8. The method of producing a reticular structure according to claim 1, wherein, after the step of withdrawing said refractory mold from said first container, said foam pre-structure protrudes from said refractory mold.
9. The method of producing a reticular structure according to claim 1, wherein, subsequent to the step of infiltrating said refractory mold with said molten substance, said method includes the step of casting a solid jacket on said refractory mold with said molten substance.
10. The method of producing a reticular structure according to claim 1, wherein said foam pre-structure has a surface and wherein, subsequent to step a), said method includes a step of modifying said surface by roughening.
11. The method of producing a reticular structure according to claim 1, wherein said foam pre-structure has a surface and wherein, subsequent to step a), said method includes a step of modifying said surface by texturing.
12. The method of producing a reticular structure according to claim 1, wherein said reticular structure has a structure surface and wherein, subsequent to step h), said method includes a step of modifying said structure surface by applying a coating to said structure surface.
13. A device for producing a reticular structure according to claim 1, wherein said second container has a container wall and at least one opening for pouring in said molten substance, and has an interior space that is sufficiently large to provide a gap between said pre-heated refractory mold filled with said molten substance and said container wall.
14. The method of Claim 1, wherein said reticular structure is a metallic reticular structure and said molten substance is a molten metallic substance

18. The method of Claim 1, wherein said second container is made of a heat-resistant material.

ABSTRACT

A method of producing reticular structures, particularly metallic reticular structures, as well as a device suitable for the production thereof. The method and device enable continuous and/or automated production of such structures, and particularly, large-scale automated production of large-dimensioned reticular structures. A reticulated foam pre-structure is placed into a first container and infiltrated with a refractory material. After solidification, the mold formed by the refractory material is removed from the first container and the foam pre-structure stripped from the mold. The mold is then pre-heated and placed into a second container and infiltrated with a molten substance that forms the reticular structure when solidified. The filled mold may be covered with a solid jacket as a means of controlling the rate and progression of solidification of the molten substance to form a fine-grained, bubble-free structure.

[The invention concerns a process for the manufacture of grid structures, especially out of metal, as well as a device appropriate for it. The objective of this invention is the manufacture of grid structures to so simplify the manufacture, that an automated fabrication of these is possible. With this, the task of finding a process is given, one which allows the manufacture of grid structures with large dimensions on a large scale. Appropriate to the invention, this is attained as the following steps are executed:]

[(1) Putting of a reticulated foam pre-structure into a hinged container; (2) Infiltration of this structure with an apyrous material; (3) Solidification of the material; (4) Removal of the solidified material from the hinged container; (5) Removal of the foam pre-structure; (6) Putting in of the resulting, preheated body into a heat-proof container; (7) Infiltration of the body with a molten bath and (8) Removal of the resulting body after solidification of the molten bath and removal of the apyrous material. The device consists of an apyrous container, whose interior space is larger than the apyrous pre-heated body.]